

Description

2 Mil thick film of high performance solvent based acrylic pressure sensitive adhesive.
High temperature and plasticizer resistance.

Laminates well to a variety of materials: low perm urethane, ether, ester and PVC foams, sponge rubber, name plates, membrane switches, labels and many more.

Physical Properties

Physical Property	Test Method	Unit	Value
Thickness: Adhesive	PSTC-33, ASTM D3652	MILS	2
Peel Strength: 180° @ 121PM, 20 min, SS	PSTC-101, ASTM D3330	OZ/IN	45
Peel Strength: 180° @ 121PM, 20 min, ABS	PSTC-101, ASTM D3330	OZ/IN	24
Shear Strength: 1"x 1", 500g	PSTC-107, ASTM D3654	Min to Fail	>10,000
Polyken Probe Tack: 1 sec dwell	ASTM D2979	Grams	900
Heat Resistance: 1"x 1", 500g	ASTM D4498	°F	400

Storage and Shelf Life: Recommend consuming all materials within a year of purchase. Material should be stored at 70°F, 50% relative humidity, out of direct sunlight.

Application: Surfaces should be clean and dry before application. Avoid touching adhesive surface.

PLEASE NOTE THAT ALL DATA SHEETS ARE SUPPLIED BY LAMATEK, INC. WITH THE UNDERSTANDING THAT THE PURCHASER MUST DETERMINE THE SUITABILITY OF A PARTICULAR PRODUCT FOR ITS INTENDED PURPOSE. UNLESS OTHERWISE STATED, LAMATEK, INC. CANNOT WARRANT PRODUCTS IN THEIR APPLICATION.