



# Technical Data Sheet

20PPI  
Reticulated Foam

## Specifications

20PPI Reticulated Polyurethane Ether Filter Foam, Charcoal in Color.

## Physical Properties

Physical Property	Test Method	Unit	Value
Cell Count		PPI	20 +/-5
Density	ASTM D 3574-91	PCF	1.4 +/- .10
Compression Set @ 50% Deflection	ASTM D 3574-91	%	15 Max
Tensile Strength	ASTM D 3574-91	LB/IN	18 Min
Elongation @ Break	ASTM D 3574-91	%	180 Min
Tear Strength	ASTM D 3574-91	LB/IN	5.0 Min
Volumetric Air Flow	ASTM D 3574-91	CFM	22 +/-3.5

PLEASE NOTE THAT ALL DATA SHEETS ARE SUPPLIED BY LAMATEK, INC. WITH THE UNDERSTANDING THAT THE PURCHASER MUST DETERMINE THE SUITABILITY OF A PARTICULAR PRODUCT FOR ITS INTENDED PURPOSE. UNLESS OTHERWISE STATED, LAMATEK, INC. CANNOT WARRANT PRODUCTS IN THEIR APPLICATION.