

### Specifications

- Microcellular Urethane Foam for use in gasketing, vibration isolation and shock protection.
- Excellent compression recovery
- High energy absorption
- Low outgassing
- Good solvent resistance

### Physical Properties

Physical Property	Test Method	Unit	Value
Density	ASTM D3574	Lb./ft <sup>3</sup>	24.5 +/-10%
Standard Color		Pantone Code	Black (0426)
Compression Force Deflection Typical	STM D3489 @ 25% Compression	PSI	12-18 15.2
Compression Set @ 50% Compression, 73°F	ASTM D3574-D	% Max	4
Compression Set @ 50% Compression, 158°F	ASTM D3574-D	% Max	8
Compression Set: Autoclave then 50% Compression, 158°F	ASTM D3574-J2 & -D	% Max	5
Dimensional Stability (typical)	24 hrs @ 194°	% Max Change	5
Tensile Strength – Min. Typical	ASTM D3574-E Die A	PSI	85 140
Tensile Elongation – Min. Typical	ASTM D3574-E Die A	%	90 105
Tear Strength – Min. Typical	ASTM D624 Die C	PLI	9 17
Resilience (Ball Rebound)	ASTM D3575-H	%	16
Temperature: Continuous Use		°F	-40 to 225
Temperature: Intermittent Use Max.		°F	250
Low Flex Temperature	22 Hrs. @ -40° Mandrel Diameter = 5 x Thickness		No Cracking